CELANYL® A3 HH J6 GF18 BK 9005/1

PA66-GF18 Celanese

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 1.80 MPa	**243**	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**260**	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	**1210**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.