ECOMID® ARX H GF20 BK 9005

PA66-GF20 Celanese

Product Texts

Car industry, Household appliances, Electrical devices.

Flammability @3.2mm nom. thickn.	HB	-

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
[C] Molding shrinkage, parallel	**0.7 / ***	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**1.1 / ***	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**6100 / -**	MPa	ISO 527
[C] Stress at break	**105 / -**	MPa	ISO 527
[C] Strain at break	**3 / -**	%	ISO 527
[C] Charpy impact strength, +23°C	**40 / -**	kJ/m²	ISO 179/1eU
[C] Charpy impact strength, -30°C	**34 / -**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**5 / -**	kJ/m²	ISO 179/1eA
[C] Charpy notched impact strength, -30°C	**4 / -**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	**5 / ***	%	Sim. to ISO 62
[C] Humidity absorption	**1.5 / ***	%	Sim. to ISO 62
[C] Density	**- / 1260**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black

Applications

Automotive, Electrical and Electronical

Certifications

Recycled Resin Content

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.