FRIANYL® A3 GF20 V2XI NC 1101/E

PA66-GF20 Celanese

Product Texts

Designed for Electrical applications requiring self-extinguishing properties combined with ignition resistance, this grade meets the most stringent safety requirements for insulating materials for the household appliance industry.

Flammability @3.2mm nom. thickn.	V-0	-
Flammability @0.4mm nom. thickn.	V-2	UL recognition (0.4)

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
[C] Molding shrinkage, parallel	**0.5 / ***	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**0.7 / ***	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**6800 / -**	MPa	ISO 527
[C] Charpy impact strength, +23°C	**40 / -**	kJ/m²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 1.80 MPa	**225 / ***	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**250 / ***	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	**4 / ***	%	Sim. to ISO 62
[C] Humidity absorption	**1.1 / ***	%	Sim. to ISO 62
[C] Density	**- / 1490**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Applications
Electrical and Electronical

Delivery form
Granules, Natural Color

Regional Availability
Europe, Asia Pacific

Special Characteristics
Heat stabilized or stable to heat

Other text information

Injection molding

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.
The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.
PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorbs moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.