

Product Texts

LNP THERMOCOMP RF004 compound is based on Nylon 6/6 resin containing 20% glass fiber.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.5	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7150	MPa	ISO 527
Stress at break	159	MPa	ISO 527
Strain at break	3.7	%	ISO 527
Flexural modulus	7000	MPa	ISO 178
Flexural strength	241	MPa	ISO 178
Izod impact strength, +23°C, 4mm	56	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	7	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	7170	MPa	ASTM D 638
Tensile Strength at Break	156	MPa	ASTM D 638
Elongation at Break	3.6	%	ASTM D 638
Flexural Modulus	5860	MPa	ASTM D 790
Flexural Strength	230	MPa	ASTM D 790
Izod Impact notched, 1/8 in	101	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	833	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	221	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	247	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ISO 1183
Water Absorption, 24hr	0.8	%	ASTM D 570
Density	1290	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America