

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	10000	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	4.5	%	ISO 527
Flexural modulus, 23°C	8500	MPa	ISO 178
Flexural strength	200	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	L 100	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	225	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250	°C	ISO 75-1/-2
Vicat softening temperature, A	245	°C	ISO 306
Vicat softening temperature, B	230	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	3	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-13
GWIT - thickness tested (2)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	930	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Comparative tracking index	400	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1530	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	280 - 300	°C	-
Mold temperature	90	°C	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America

**Certifications**

RoHS compliant