

EMLON 66 GFR 25 FR V0

PA66-GF25

Emas Plastik San.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	6500	MPa	ISO 527
Tensile Strength	120	MPa	ISO 527
Strain at break	5	%	ISO 527
Izod notched impact strength, +23°C	12	kJ/m ²	ISO 180/1A
Shore D hardness	80	-	ISO 7619-1
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	265	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	245	°C	ISO 75-1/-2
Vicat softening temperature, B	255	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Other properties			
Density	1290	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	250 - 300	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

Europe, Near East/Africa

Special Characteristics

Flame retardant