

EPLAMID 66 GV0 25 NC Q1C5C001

PA66-GF25

Epsan Plastik San. Tic. A.Ş

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	9400	MPa	ISO 527
Stress at break	150	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	8600	MPa	ISO 178
Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Comparative tracking index	250	-	IEC 60112
Other properties			
Density	1550	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	280	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Delivery form

Natural Color

Regional Availability

Europe