

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>85 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>275 / *</b>	°C	-
Load	<b>5 / *</b>	kg	-

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>8400 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>105 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>30 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>4 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>- / 1390</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Special Characteristics**

Flame retardant

**Regional Availability**

Asia Pacific