

LUVOCOM 1114-0717

(PAEK+PTFE)-CF

LEHVOSS Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Thermal conductivity of melt	0.6	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17000	MPa	ISO 527
Tensile Strength	180	MPa	ISO 527
Flexural modulus, 23°C	14000	MPa	ISO 178
Charpy impact strength, -30°C	20	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	305	°C	ISO 75-1/-2
Vicat softening temperature, A	320	°C	ISO 306
Coeff. of linear therm. expansion, parallel	5	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	100000	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1510	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.05	%	-
Melt temperature	390	°C	-
Mold temperature	160 - 230	°C	-
Zone 1	370 - 420	°C	-
Zone 2	380 - 420	°C	-
Zone 3	390 - 420	°C	-
Nozzle temperature	390 - 420	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Increased electrical conductivity

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Applications

Aircraft and Aerospace, Automotive, Electrical and Electrical, Medical

Regional Availability

North America, Europe, Asia Pacific