

SCHULAMID® 66 GF 25

PA66-GF25

LyondellBasell Industries

Mechanical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	9.5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Density	1320 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	140 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America