

Staramide RF005Z

PA66-GF25

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	150	MPa	ISO 527
Strain at break	2.8	%	ISO 527
Flexural modulus, 23°C	6600	MPa	ISO 178
Izod impact strength, +23°C	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	232	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Features

Low Odor

Delivery form

Pellets

Regional Availability

Europe