

**Product Texts**

Starflam 525K NT0779 (formerly Vydyne® ECO525K NT0779) is a non-halogenated flame retardant, PA66 grade modified with 25% glass fiber for improved stiffness and strength.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>0.3 / *</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>1.1 / *</b>	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>8700 / 7100</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>132 / 97</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>3.1 / 3.2</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>68 / 73</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>66 / 63</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>10 / 14</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>9.5 / 9</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>239 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>257 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>23 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>67 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>V-0 / *</b>	class	IEC 60695-11-10

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Electric strength	<b>42 / -</b>	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>1 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>1.9 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1400 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Special Characteristics**

Flame retardant, Halogen-free

**Regional Availability**

North America, Europe, Asia Pacific