

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	165 / 135	MPa	ISO 527
Strain at break	3 / 3	%	ISO 527
Flexural modulus, 23°C	9300 / 6500	MPa	ISO 178
Flexural modulus	5500 / -	MPa	ISO 178
Flexural modulus temperature	80	°C	-
Charpy impact strength, +23°C	65 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9.5 / 14	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	R 121	-	ISO 2039-2

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	265 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	241 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Dissipation factor, 1MHz	100 / -	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
Electric strength	38 / 33	kV/mm	IEC 60243-1

Other properties	dry / cond	Unit	Test Standard
Water absorption	4 / *	%	Sim. to ISO 62
Density	1590 / -	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Special Characteristics

Flame retardant

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa