

**DURANEX® 304SA**

(PBT+ABS)-GF15

Polyplastics

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>96</b>	MPa	ISO 527
Strain at break	<b>2.3</b>	%	ISO 527
Flexural modulus, 23°C	<b>5310</b>	MPa	ISO 178
Flexural strength	<b>139</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	<b>M 80</b>	-	ISO 2039-2

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>120</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>40</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>80</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Yellow Card available	<b>yes</b>	-	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>4E14</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>24</b>	kV/mm	IEC 60243-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1280</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Features**

Low Warpage

**Regional Availability**

Asia Pacific