

**Product Texts**

LNP THERMOCOMP RF006LXP compound is based on Nylon 6/6 resin containing 30% glass fiber. Added features of this grade include: Low Extractables.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.4	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	10300	MPa	ASTM D 638
Tensile Strength at Break	155	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	8820	MPa	ASTM D 790
Flexural Strength	224	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	752	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	246	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1590	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America