

Product Texts

LNP THERMOCOMP RZ006 compound is based on Nylon 6/6 resin containing 30% milled glass.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	1.4	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.5	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	68	MPa	ASTM D 638
Elongation at Break	4.3	%	ASTM D 638
Flexural Modulus	4300	MPa	ASTM D 790
Flexural Strength	119	MPa	ASTM D 790
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	320	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	115	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific