

NRB5430G-NA

PA66-GF30

Pontex Polyblend Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	98.1	MPa	ASTM D 638
Flexural Modulus	8829	MPa	ASTM D 790
Flexural Strength	157	MPa	ASTM D 790
Izod Impact notched, 1/8 in	78.5	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	3.2	mm	-
DTUL @ 264 psi	240	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Flame retardant, Halogen-free

Regional Availability

Asia Pacific