

PENTAMID A GV30 H

PA66-GF30

Pentac Polymer GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	10000 / 7500	MPa	ISO 527
Stress at break	190 / 130	MPa	ISO 527
Strain at break	3.5 / 5	%	ISO 527
Charpy impact strength, +23°C	85 / 95	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	13 / 15	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Water absorption	5.2 / *	%	Sim. to ISO 62
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m ³	ISO 1183

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	140 / *	cm ³ /g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3	h	-
Processing humidity	≤0.13	%	-
Mold temperature	60 - 100	°C	-
Feed temperature	80	°C	-
Zone 1	270	°C	-
Zone 2	280	°C	-
Zone 3	285	°C	-
Zone 4	290	°C	-
Zone 5	285	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Pellets

Regional Availability

Europe

Special Characteristics

Heat stabilized or stable to heat