

Product Texts

The production of Recomyde generates 90% less CO2 emissions than standard PA compounds.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9500 / 7000	MPa	ISO 527
Tensile Strength	150 / 100	MPa	ISO 527
Strain at break	2.5 / 5	%	ISO 527
Flexural modulus, 23°C	9000 / 6500	MPa	ISO 178
Flexural strength	190 / 120	MPa	ISO 178
Charpy impact strength, +23°C	50 / 75	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8 / 15	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m ³	ISO 1183

Characteristics

Certifications

Recycled Resin Content, ISCC Plus

Regional Availability

Europe