

**Product Texts**

Polyamide 66, 30% glass fiber reinforced, heat-aging stabilized, hydrolysis stabilized, for injection molding, black. For Asian availability only.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10100 / 7300	MPa	ISO 527
<sup>[C]</sup> Stress at break	190 / 140	MPa	ISO 527
<sup>[C]</sup> Strain at break	3 / 6	%	ISO 527
Flexural modulus, 23°C	9100 / 6500	MPa	ISO 178
Flexural strength	280 / 190	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	80 / 90	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	70 / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	10 / 15	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	9 / -	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	255 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	255 / *	°C	ISO 306
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	400 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1360 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Heat stabilized or stable to heat

**Chemical Resistance**

Hydrolytically Stable

**Regional Availability**

Asia Pacific