

**Product Texts****Zytel® FG70G30HSR3 BK309 is a 30% Glass Reinforced, Heat Stabilized, Polyamide 66**

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1200	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.22	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2220	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	6.85E-8	m <sup>2</sup> /s	-
<sup>[C]</sup> Ejection temperature	210	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10000 / 7000	MPa	ISO 527
<sup>[C]</sup> Stress at break	200 / 130	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.1 / 5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	60 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	50 / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	11 / 14	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	209 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	28 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	95 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Oxygen index	24 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1370 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Delivery form**

Pellets, Black

**Regional Availability**

Europe

**Additives**

Release agent