

**DOMAMID 66G33H1**

PA66-GF33

DOMO Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	10000	MPa	ISO 527
Stress at break	185	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	8700	MPa	ISO 178
Charpy impact strength, +23°C	70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2
Vicat softening temperature, B	255	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1380	kg/m <sup>3</sup>	ISO 1183

Material specific properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	145	cm <sup>3</sup> /g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	90 - 110	°C	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific

**Special Characteristics**

Heat stabilized or stable to heat