

**Hylon® N1033STL**

PA66-GF33

Ravago Manufacturing Americas

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>0.5 / *</b>	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	<b>120 / -</b>	MPa	ISO 527
Strain at break	<b>3.2 / -</b>	%	ISO 527
Flexural modulus, 23°C	<b>7100 / -</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>18 / -</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>124 / 100</b>	MPa	ASTM D 638
Elongation at Break	<b>3 / 5</b>	%	ASTM D 638
Flexural Modulus	<b>6550 / 5520</b>	MPa	ASTM D 790
Flexural Strength	<b>193 / 145</b>	MPa	ASTM D 790
Rockwell Hardness	<b>M 82 / M 60</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>190 / 210</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>236 / *</b>	°C	ISO 75-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>31</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>238</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>22 / -</b>	kV/mm	ASTM D 149
Volume Resistivity	<b>1E15 / -</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1330 / -</b>	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	<b>0.4</b>	%	ASTM D 570
Density	<b>1330</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Additives**

Lubricants

**Delivery form**

Pellets

**Regional Availability**

North America