

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10000 / 8000	MPa	ISO 527
^[C] Stress at break	190 / 135	MPa	ISO 527
^[C] Strain at break	3 / 5	%	ISO 527
Flexural modulus, 23°C	9000 / 6800	MPa	ISO 178
Flexural strength	275 / 202	MPa	ISO 178
^[C] Charpy impact strength, +23°C	72 / 83	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11 / 16	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 120	-	ISO 2039-2
ASTM Data			
Tensile Strength	186 / 132	MPa	ASTM D 638
Elongation at Break	3 / 5	%	ASTM D 638
Flexural Modulus	9300 / 6300	MPa	ASTM D 790
Flexural Strength	289 / 216	MPa	ASTM D 790
Rockwell Hardness	M 96 / M 75	-	ASTM D 785
Izod Impact notched, 1/8 in	127 / 147	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	265 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
Coefficient of Thermal Expansion, MD	30.1	E-6/K	ASTM D 696
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	250	°C	ASTM D 648
Thermal Conductivity, solid state	0.0432	W/(m K)	ASTM C 177
Specific Heat	1590	J/(kg K)	ASTM C 351
Limiting Oxygen Index	23	%	ASTM D 2863

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	28 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	425 / -	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	28 / -	kV/mm	ASTM D 149
Volume Resistivity	1E15 / -	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	1.7 / *	%	Sim. to ISO 62
^[C] Density	1390 / -	kg/m ³	ISO 1183
Density	1390	kg/m ³	ASTM D 792

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 3	h	-

Melt temperature	275 - 295	°C	-
Mold temperature	75 - 85	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive

Regional AvailabilityNorth America, Europe, Asia Pacific, South and Central America,
Near East/Africa