

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	135	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	9200	MPa	ISO 178
Flexural strength	250	MPa	ISO 178
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific