

Lucent PA G66-33

PA66-GF33

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	138	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	7584	MPa	ASTM D 790
Flexural Strength	221	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	243	°C	ASTM D 648
Melting Temperature	257	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America