

| <b>Mechanical properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|------------------------------|--------------|-------------|----------------------|
| <b>ASTM Data</b>             |              |             |                      |
| Tensile Strength at Yield    | <b>172</b>   | MPa         | ASTM D 638           |
| Elongation at Break          | <b>3</b>     | %           | ASTM D 638           |
| Flexural Modulus             | <b>8615</b>  | MPa         | ASTM D 790           |
| Flexural Strength            | <b>241</b>   | MPa         | ASTM D 790           |
| Izod Impact notched, 1/8 in  | <b>107</b>   | J/m         | ASTM D 256           |

| <b>Thermal properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|---------------------------|--------------|-------------|----------------------|
| <b>ASTM Data</b>          |              |             |                      |
| Melting Temperature       | <b>260</b>   | °C          | ASTM D 3418          |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>1380</b>  | kg/m <sup>3</sup> | ASTM D 792           |

**Characteristics**

**Delivery form**

Natural Color

**Regional Availability**

Europe, Asia Pacific

**Certifications**

RoHS compliant