

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0037	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	193	MPa	ASTM D 638
Elongation at Break	3.6	%	ASTM D 638
Flexural Modulus	9304	MPa	ASTM D 790
Flexural Strength	317	MPa	ASTM D 790
Izod Impact notched, 1/8 in	144	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	260	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics

Delivery form
Natural Color

Regional Availability
Europe, Asia Pacific

Certifications
RoHS compliant