

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10000	MPa	ISO 527
Stress at break	190	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	9300	MPa	ISO 178
Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	70	kJ/m ²	ISO 180/1U

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	263	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	65 - 82	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.2	%	-
Melt temperature	287 - 316	°C	-
Mold temperature	82 - 93	°C	-
Zone 1	260 - 293	°C	-
Zone 2	277 - 299	°C	-
Zone 3	282 - 310	°C	-
Nozzle temperature	279 - 307	°C	-
Injection pressure	5 - 15	MPa	-
Back pressure	0 - 50	MPa	-
Holding pressure	4 - 12	MPa	-
Maximum residence time	6	min	-

Characteristics

Processing

Injection Molding

Applications

Automotive

Chemical Resistance

Hydrolytically Stable

Regional Availability

North America