

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0085	mm/mm	ASTM D 955
Mechanical properties	dry / cond	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	150 / 120	MPa	ASTM D 638
Elongation at Break	4 / 6	%	ASTM D 638
Flexural Modulus	10500 / 7500	MPa	ASTM D 790
Flexural Strength	240 / 200	MPa	ASTM D 790
Rockwell Hardness	R 120 /	-	ASTM D 785
Izod Impact notched, 1/8 in	108 / 157	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	245	°C	ASTM D 648
DTUL @ 264 psi	258	°C	ASTM D 648
Melting Temperature	262	°C	ASTM D 3418
Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13 / 1E13	Ohm*m	IEC 62631-3-1
Electric strength	26 / 24	kV/mm	IEC 60243-1
Comparative tracking index	650 / -	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	2.1	%	ASTM D 570
Water Absorption, Equilibrium	6.5	%	ASTM D 570
Density	1390	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Applications

Automotive, Electrical and Electronical, Encapsulation

### Delivery form

Black

### Regional Availability

Asia Pacific