

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	140	MPa	ISO 527
Flexural modulus, 23°C	8300	MPa	ISO 178
Flexural strength	200	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1370	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Applications

Automotive

### Special Characteristics

High impact or impact modified

### Regional Availability

North America