

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	11600 / 8400	MPa	ISO 527
Stress at break	215 / 145	MPa	ISO 527
Strain at break	3 / 5	%	ISO 527
Flexural modulus, 23°C	10000 / 8000	MPa	ISO 178
Flexural strength	300 / 245	MPa	ISO 178
Charpy impact strength, +23°C	92 / 102	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	90 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	15 / 19	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	13 / -	kJ/m ²	ISO 179/1eA
Ball indentation hardness	255 / -	MPa	ISO 2039-1
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	255 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	22 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	67 / *	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.6	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E11 / 1E8	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	600 / -	-	IEC 60112
Other properties			
Water absorption	5.3 / *	%	Sim. to ISO 62
Density	1400 / -	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Natural Color

Regional Availability

Europe, Asia Pacific

Special Characteristics

Heat stabilized or stable to heat