

**AKROMID® A28 GF 35 1 natural (5202)**

PA66-GF35

Akro-Plastic GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	12000	MPa	ISO 527
Stress at break	225	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	10000	MPa	ISO 178
Charpy impact strength, +23°C	90	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	255	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1400	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Delivery form**

Natural Color

**Regional Availability**

Europe, Asia Pacific

**Special Characteristics**

Heat stabilized or stable to heat