

**Bergamid™ A700 G35 U-S0 NC003**

PA66-GF35

Avient Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>160</b>	MPa	ASTM D 638
Flexural Modulus	<b>9500</b>	MPa	ASTM D 790
Flexural Strength	<b>250</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>90</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-
DTUL @ 264 psi	<b>245</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	<b>1E15</b>	Ohm	ASTM D 257
<b>Other properties</b>			
Density	<b>1460</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80 - 90</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Mold temperature	<b>65 - 85</b>	°C	-
Zone 1	<b>260 - 280</b>	°C	-
Zone 2	<b>260 - 280</b>	°C	-
Zone 3	<b>260 - 280</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific

**Delivery form**

Natural Color