

Product Texts

Injection Molding, 35% Glass Reinforced, Heat Stabilized, Excellent Surface Properties, Recycled Content

ISO 1043 PA66-GF35

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11200 / 7500	MPa	ISO 527
^[C] Stress at break	190 / 130	MPa	ISO 527
^[C] Strain at break	3 / 5	%	ISO 527
^[C] Tensile creep modulus, 1h	* / 7000	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	* / 5800	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	80 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	70 / 75	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 20	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10 / 10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
^[C] Oxygen index	23 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	4 / 10	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	4 / 4	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	110 / 2100	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	150 / 650	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
^[C] Electric strength	35 / 30	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.8 / *	%	Sim. to ISO 62
^[C] Density	1410 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	290	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Certifications

Recycled Resin Content

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 280 - 300 °C

Mold temperature: 80 - 120 °C