

Product Texts

LNP THERMOCOMP RF007SXP compound is based on Nylon 6/6 resin containing 35% glass fiber. Added features of this grade include: Heat Stabilized.

UL Yellow Card Link [E121562-101281587](https://www.ulprospector.com/121562-101281587)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.35	mm/mm	ASTM D 955
Mold Shrinkage, TD	2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11200	MPa	ISO 527
Yield stress	185	MPa	ISO 527
Yield strain	2.6	%	ISO 527
Stress at break	185	MPa	ISO 527
Strain at break	2.6	%	ISO 527
Flexural modulus	9440	MPa	ISO 178
Flexural strength	266	MPa	ISO 178
Izod impact strength, +23°C, 4mm	55	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	11380	MPa	ASTM D 638
Tensile Strength at Yield	185	MPa	ASTM D 638
Tensile Strength at Break	185	MPa	ASTM D 638
Elongation at Yield	2.5	%	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	8100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	78	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	788	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	245	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	258	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
Coefficient of Thermal Expansion, MD	25	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	73.1	E-6/K	ASTM D 696
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	252	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	1	%	Sim. to ISO 62
Water Absorption, 24hr	0.73	%	ASTM D 570
Density	1420	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-

Back pressure

0.2 - 0.3

MPa

-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific