

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	210	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	10000	MPa	ISO 178
Flexural strength	300	MPa	ISO 178
Izod notched impact strength, +23°C	15	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1410	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance, Hydrolytically Stable

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific