

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	200	MPa	ISO 527
Yield strain	3	%	ISO 527
Flexural strength	300	MPa	ISO 178
Izod notched impact strength, +23°C	17	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	252	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1410	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	70 - 120	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, South and Central America

Delivery form

Natural Color