

PENTAMID A GV35 H black

PA66-GF35

Pentac Polymer GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	11000 / 8600	MPa	ISO 527
Stress at break	195 / 140	MPa	ISO 527
Strain at break	3 / 4	%	ISO 527
Flexural modulus, 23°C	9400 / -	MPa	ISO 178
Flexural strength	260 / -	MPa	ISO 178
Charpy impact strength, +23°C	90 / 95	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	14 / 19	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Water absorption	5 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	140 / *	cm ³ /g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3	h	-
Processing humidity	≤0.13	%	-
Mold temperature	60 - 100	°C	-
Feed temperature	80	°C	-
Zone 1	270	°C	-
Zone 2	280	°C	-
Zone 3	285	°C	-
Zone 4	290	°C	-
Zone 5	285	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

Heat stabilized or stable to heat

Certifications

RoHS compliant

Regional Availability

Europe