

POLIMID A 35 GF V0F K

PA66-GF35

Poliblend S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	9500	MPa	ISO 527
Yield stress	150	MPa	ISO 527
Yield strain	2	%	ISO 527
Stress at break	150	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod impact strength, +23°C	90	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	10.5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	248	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Comparative tracking index	550	-	IEC 60112
Other properties			
Density	1440	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant

Regional Availability

Europe