

Taromid A 280 G7

PA66-GF35

Taro Plast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	280	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	10500	MPa	ISO 527
Stress at break	190	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Flexural modulus, 23°C	10000	MPa	ISO 178
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	125	J/m	ASTM D 256
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	256	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	246	°C	ISO 75-1/-2
Vicat softening temperature, B	255	°C	ISO 306
Coeff. of linear therm. expansion, parallel	26	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
Limiting Oxygen Index	27	%	ASTM D 2863
Electrical properties			
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	26	kV/mm	IEC 60243-1
Comparative tracking index	550	-	IEC 60112
Other properties			
Water absorption	4.5	%	Sim. to ISO 62
Density	1360	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Features

Low Odor

Additives

Release agent

Regional Availability

Europe

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat