

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11400 / 7000	MPa	ISO 527
^[C] Stress at break	200 / 120	MPa	ISO 527
^[C] Strain at break	3 / 7.3	%	ISO 527
Flexural modulus, 23°C	9000 / 5400	MPa	ISO 178
Flexural strength	270 / 170	MPa	ISO 178
^[C] Charpy impact strength, +23°C	80 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 18	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	245 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	257 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	4E12 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 6E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1410 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Special Characteristics
Heat stabilized or stable to heat

Delivery form
Black

Applications
Automotive, General Purpose