Crastin® LW9020 NC010

(PBT+ASA)-GF20 Celanese

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.
If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® LW9020 NC010 is a 20% glass fiber reinforced polybutylene terephthalate blend for injection molding. It has improved surface aesthetics, excellent dimensional stability and low warpage characteristics.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
[C] Molding shrinkage, parallel	**0.3**	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**0.7**	%	ISO 294-4, 2577
[C] Density of melt	**1190**	kg/m³	-
[C] Thermal conductivity of melt	**0.25**	W/(m K)	-
[C] Spec. heat capacity of melt	**1850**	J/(kg K)	-
[C] Ejection temperature	**170**	°C	-
ASTM Data			
Mold Shrinkage, MD	**0.003**	mm/mm	ASTM D 955
Mold Shrinkage, TD	**0.006**	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**7000**	MPa	ISO 527
[C] Stress at break	**110**	MPa	ISO 527
[C] Strain at break	**2.9**	%	ISO 527
[C] Tensile creep modulus, 1h	**6500**	MPa	ISO 899-1
[C] Tensile creep modulus, 1000h	**4800**	MPa	ISO 899-1
[C] Charpy impact strength, +23°C	**60**	kJ/m²	ISO 179/1eU
[C] Charpy impact strength, -30°C	**43**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**9.5**	kJ/m²	ISO 179/1eA
[C] Charpy notched impact strength, -30°C	**7.5**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Melting temperature, 10°C/min	**225**	°C	ISO 11357-1/-3
[C] Glass transition temperature, 10°C/min	**120**	°C	ISO 11357-1/-2
[C] Temp. of deflection under load, 1.80 MPa	**150**	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**210**	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	**145**	°C	ISO 306
[C] Coeff. of linear therm. expansion, parallel	**30**	E-6/K	ISO 11359-1/-2
[C] Coeff. of linear therm. expansion, normal	**100**	E-6/K	ISO 11359-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	**HB**	class	IEC 60695-11-10
Thickness tested	**1.5**	mm	-
Yellow Card available	**yes**	-	-
[C] Burning Behav. at thickness h	**HB**	class	IEC 60695-11-10
Thickness tested	**0.8**	mm	-
Yellow Card available	**yes**	-	-
[C] Burning rate, FMVSS, Thickness 1 mm	**38**	mm/min	ISO 3795 (FMVSS 302)
[C] Oxygen index	**19**	%	ISO 4589-1/-2

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

ASTM Data			
UL 94 Flame rating	**HB**	-	UL 94
Thickness tested	**1.5**	mm	-
Coefficient of Thermal Expansion, MD	**30**	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	**100**	E-6/K	ASTM D 696

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
[C] Relative permittivity, 100Hz	**3.7**	-	IEC 62631-2-1
[C] Relative permittivity, 1MHz	**3.4**	-	IEC 62631-2-1
[C] Dissipation factor, 100Hz	**20.1**	E-4	IEC 62631-2-1
[C] Dissipation factor, 1MHz	**180**	E-4	IEC 62631-2-1
[C] Volume resistivity	**>1E13**	Ohm*m	IEC 62631-3-1
[C] Surface resistivity	**1E14**	Ohm	IEC 62631-3-2
[C] Electric strength	**35**	kV/mm	IEC 60243-1
[C] Comparative tracking index	**550**	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Water absorption	**0.78**	%	Sim. to ISO 62
[C] Humidity absorption	**0.26**	%	Sim. to ISO 62
[C] Density	**1350**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Delivery form
Pellets, Natural Color

Additives
Lubricants, Release agent

Features
Low Warpage, Weldable

Chemical Resistance
General Chemical Resistance

Applications
Automotive

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.