Vydyne® R535H BK02

PA66-GF35 Ascend

Product Texts

Vydyne R535H BK02 is a general purpose, 35% glass-filled, heat-stabilized PA66 based resin designed for injection molding applications. R535H BK02 offers improved flow with a black surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
[C] Molding shrinkage, parallel	**0.4 / ***	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**0.9 / ***	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**10600 / 8000**	MPa	ISO 527
[C] Stress at break	**212 / 136**	MPa	ISO 527
[C] Strain at break	**2.9 / 5.5**	%	ISO 527
Flexural modulus, 23°C	**10500 / 7000**	MPa	ISO 178
Flexural strength	**300 / 205**	MPa	ISO 178
[C] Charpy impact strength, +23°C	**80 / 90**	kJ/m²	ISO 179/1eU
[C] Charpy impact strength, -30°C	**70 / 85**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**12 / 14**	kJ/m²	ISO 179/1eA
[C] Charpy notched impact strength, -30°C	**11 / 12**	kJ/m²	ISO 179/1eA
Izod notched impact strength, +23°C	**12 / 14**	kJ/m²	ISO 180/1A
Izod notched impact strength	**11 / 12**	kJ/m²	ISO 180/1A
Temperature	**-30**	°C	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Melting temperature, 10°C/min	**260 / ***	°C	ISO 11357-1/-3
[C] Temp. of deflection under load, 1.80 MPa	**250 / ***	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**260 / ***	°C	ISO 75-1/-2
[C] Coeff. of linear therm. expansion, parallel	**20 / ***	E-6/K	ISO 11359-1/-2
[C] Coeff. of linear therm. expansion, normal	**110 / ***	E-6/K	ISO 11359-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	**HB / ***	class	IEC 60695-11-10
Thickness tested	**1.5 / ***	mm	-
[C] Burning Behav. at thickness h	**HB / ***	class	IEC 60695-11-10
Thickness tested	**0.8 / ***	mm	-
Glow Wire Flammability Index (GWFI)	**700**	°C	IEC 60695-2-12
GWFI - thickness tested (1)	**0.75**	mm	-
Glow Wire Flammability Index (GWFI)	**700**	°C	IEC 60695-2-12
GWFI - thickness tested (2)	**1.5**	mm	-
Glow Wire Flammability Index (GWFI)	**875**	°C	IEC 60695-2-12
GWFI - thickness tested (3)	**3**	mm	-
Glow Wire Ignition Temperature (GWIT)	**725**	°C	IEC 60695-2-13
GWIT - thickness tested (1)	**0.75**	mm	-
Glow Wire Ignition Temperature (GWIT)	**725**	°C	IEC 60695-2-13
GWIT - thickness tested (2)	**1.5**	mm	-
Glow Wire Ignition Temperature (GWIT)	**750**	°C	IEC 60695-2-13
GWIT - thickness tested (3)	**3**	mm	-
ASTM Data			
UL 94 Flame rating	**HB**	-	UL 94
Thickness tested	**0.75**	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Volume resistivity	**1E11 / -**	Ohm*m	IEC 62631-3-1
[C] Electric strength	**31 / 20**	kV/mm	IEC 60243-1

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

[C] Comparative tracking index	**325 / -**	-	IEC 60112
ASTM Data			
Arc Resistance	**90 / -**	s	ASTM D 495

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	**0.8 / ***	%	Sim. to ISO 62
[C] Humidity absorption	**1.6 / ***	%	Sim. to ISO 62
[C] Density	**1410 / -**	kg/m³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**80**	°C	-
Pre-drying - Time	**4**	h	-
Melt temperature	**285 - 305**	°C	-
Mold temperature	**65 - 95**	°C	-
Zone 1	**280 - 310**	°C	-
Zone 2	**280 - 310**	°C	-
Zone 3	**280 - 310**	°C	-
Nozzle temperature	**280 - 310**	°C	-

Characteristics

Processing
Injection Molding

Features
Fatigue Resistance

Delivery form
Pellets, Black

Chemical Resistance
General Chemical Resistance, Solvent Resistance, Oil Resistance

Additives
Lubricants

Applications
Automotive, General Purpose

Special Characteristics
Heat stabilized or stable to heat

Regional Availability
North America, Europe, Asia Pacific

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.