

**Product Texts**

Vydyne R535H NT651 is a natural, 35% glass-filled PA66 resin. It is heat stabilized with an electrically neutral heat stabilizer and designed for electrical applications requiring high dielectric strength, low conductivity, and corrosion resistance.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	11800 / 9500	MPa	ISO 527
<sup>[C]</sup> Stress at break	210 / 150	MPa	ISO 527
<sup>[C]</sup> Strain at break	3 / 2.9	%	ISO 527
Flexural modulus, 23°C	10500 / 6000	MPa	ISO 178
Flexural strength	300 / 140	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	68 / 89	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	60 / 75	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	12 / 16	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	14 / 18	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	12 / 12	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	252 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	18.9 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	74.7 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Glow Wire Flammability Index (GWFI)	750	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.75	mm	-
Glow Wire Flammability Index (GWFI)	725	°C	IEC 60695-2-12
GWFI - thickness tested (2)	1.5	mm	-
Glow Wire Flammability Index (GWFI)	800	°C	IEC 60695-2-12
GWFI - thickness tested (3)	3	mm	-
Glow Wire Ignition Temperature (GWIT)	775	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.75	mm	-
Glow Wire Ignition Temperature (GWIT)	725	°C	IEC 60695-2-13
GWIT - thickness tested (2)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-

**ASTM Data**

UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E12 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	20 / -	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

**ASTM Data**

Arc Resistance	150 / -	s	ASTM D 495
----------------	---------	---	------------

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	0.8 / *	%	Sim. to ISO 62
[C] Humidity absorption	1.6 / *	%	Sim. to ISO 62
[C] Density	1410 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	280 - 310	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	280 - 310	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Additives**

Lubricants

**Special Characteristics**

Heat stabilized or stable to heat

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific