

Product Texts

Vydyne R535XHT BK0761 is a 35% glass-filled, heat-stabilized PA66 based resin, specifically designed to withstand long term exposure to elevated temperatures up to 210°C.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11000 / 8200	MPa	ISO 527
^[C] Stress at break	193 / 134	MPa	ISO 527
^[C] Strain at break	3.4 / 4.2	%	ISO 527
^[C] Charpy impact strength, +23°C	90 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	83 / 83	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	14 / 18	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11 / 11	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	254 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	18 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	73 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Electric strength	36 / 29	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1.6 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.7 / *	%	Sim. to ISO 62
^[C] Density	1430 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific