

Product Texts

LNP THERMOCOMP RF008 compound is based on Nylon 6/6 resin containing 40% glass fiber.

UL Yellow Card Link [E207780-103093631](https://www.ul.com/yellowcard/E207780-103093631)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.3	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	12200	MPa	ISO 527
Stress at break	188	MPa	ISO 527
Strain at break	2.7	%	ISO 527
Flexural modulus	12100	MPa	ISO 178
Izod impact strength, +23°C, 4mm	74	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	13	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	13300	MPa	ASTM D 638
Tensile Strength at Break	185	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	10400	MPa	ASTM D 790
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1120	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	242	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	26.8	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	59.2	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
DTUL @ 264 psi	253	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1470	kg/m ³	ISO 1183
Water Absorption, 24hr	0.6	%	ASTM D 570
Density	1480	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific