

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	12000	MPa	ISO 527
Stress at break	230	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	11500	MPa	ISO 178
Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	258	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	244	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1450	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	290 - 320	°C	-
Mold temperature	90	°C	-
Back pressure	1	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa