

**SLOVAMID®66 GF 40 E/1M**

PA66-GF40

Plastcom, spol. s r.o.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>10</b>	g/10min	ISO 1133
Temperature	<b>275</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>13000</b>	MPa	ISO 527
Tensile Strength	<b>160</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>7700</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>60</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>9</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>260</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>255</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>250</b>	°C	ISO 306
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Electric strength	<b>25</b>	kV/mm	IEC 60243-1
<b>Other properties</b>			
Density	<b>1460</b>	kg/m <sup>3</sup>	ISO 1183
Moisture Content	<b>0.15</b>	%	-

**Characteristics****Processing**

Injection Molding, Profile Extrusion, Other Extrusion

**Regional Availability**

Europe

**Delivery form**

Black, Natural Color