

**Product Texts**

Vydyne R543H Natural is a general purpose, 43% glass-filled, heat-stabilized, high viscosity PA66 based resin designed for injection molding applications. R543H Natural offers standard flow with a natural surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

| Processing/Physical Characteristics        | dry / cond | Unit | Test Standard   |
|--|------------|------|-----------------|
| <b>ISO Data</b>                            |            |      |                 |
| <sup>[C]</sup> Molding shrinkage, parallel | 0.4 / *    | %    | ISO 294-4, 2577 |
| <sup>[C]</sup> Molding shrinkage, normal   | 0.9 / *    | %    | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties                                | dry / cond    | Unit              | Test Standard |
|--|---------------|-------------------|---------------|
| <b>ISO Data</b>                                      |               |                   |               |
| <sup>[C]</sup> Tensile Modulus                       | 14800 / 11300 | MPa               | ISO 527       |
| <sup>[C]</sup> Stress at break                       | 225 / 170     | MPa               | ISO 527       |
| <sup>[C]</sup> Strain at break                       | 3 / 4         | %                 | ISO 527       |
| Flexural modulus, 23°C                               | 12500 / 9400  | MPa               | ISO 178       |
| Flexural strength                                    | 340 / 250     | MPa               | ISO 178       |
| <sup>[C]</sup> Charpy impact strength, +23°C         | 92 / 95       | kJ/m <sup>2</sup> | ISO 179/1eU   |
| <sup>[C]</sup> Charpy impact strength, -30°C         | 87 / 90       | kJ/m <sup>2</sup> | ISO 179/1eU   |
| <sup>[C]</sup> Charpy notched impact strength, +23°C | 14 / 20       | kJ/m <sup>2</sup> | ISO 179/1eA   |
| <sup>[C]</sup> Charpy notched impact strength, -30°C | 13 / 14       | kJ/m <sup>2</sup> | ISO 179/1eA   |
| Izod notched impact strength, +23°C                  | 13 / 19       | kJ/m <sup>2</sup> | ISO 180/1A    |
| Izod notched impact strength                         | 13 / 13       | kJ/m <sup>2</sup> | ISO 180/1A    |
| Temperature  | -30           | °C                | -             |

[C]: CAMPUS

| Thermal properties   | dry / cond | Unit  | Test Standard   |
|--|------------|-------|-----------------|
| <b>ISO Data</b>  |            |       |                 |
| <sup>[C]</sup> Melting temperature, 10°C/min               | 260 / *    | °C    | ISO 11357-1/-3  |
| <sup>[C]</sup> Temp. of deflection under load, 1.80 MPa    | 252 / *    | °C    | ISO 75-1/-2     |
| <sup>[C]</sup> Temp. of deflection under load, 0.45 MPa    | 260 / *    | °C    | ISO 75-1/-2     |
| <sup>[C]</sup> Coeff. of linear therm. expansion, parallel | 16 / *     | E-6/K | ISO 11359-1/-2  |
| <sup>[C]</sup> Coeff. of linear therm. expansion, normal   | 102 / *    | E-6/K | ISO 11359-1/-2  |
| <sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.       | HB / *     | class | IEC 60695-11-10 |
| Thickness tested   | 1.5 / *    | mm    | -               |
| <sup>[C]</sup> Burning Behav. at thickness h               | HB / *     | class | IEC 60695-11-10 |
| Thickness tested   | 0.8 / *    | mm    | -               |
| <sup>[C]</sup> Oxygen index                                | 25 / *     | %     | ISO 4589-1/-2   |
| Glow Wire Flammability Index (GWFI)                        | 675        | °C    | IEC 60695-2-12  |
| GWFI - thickness tested (1)                                | 0.75       | mm    | -               |
| Glow Wire Flammability Index (GWFI)                        | 675        | °C    | IEC 60695-2-12  |
| GWFI - thickness tested (2)                                | 1.5        | mm    | -               |
| Glow Wire Flammability Index (GWFI)                        | 960        | °C    | IEC 60695-2-12  |
| GWFI - thickness tested (3)                                | 3          | mm    | -               |
| Glow Wire Ignition Temperature (GWIT)                      | 700        | °C    | IEC 60695-2-13  |
| GWIT - thickness tested (1)                                | 0.75       | mm    | -               |
| Glow Wire Ignition Temperature (GWIT)                      | 700        | °C    | IEC 60695-2-13  |
| GWIT - thickness tested (2)                                | 1.5        | mm    | -               |
| Glow Wire Ignition Temperature (GWIT)                      | 750        | °C    | IEC 60695-2-13  |
| GWIT - thickness tested (3)                                | 3          | mm    | -               |
| <b>ASTM Data</b>   |            |       |                 |
| UL 94 Flame rating   | HB         | -     | UL 94           |
| Thickness tested   | 0.75       | mm    | -               |

[C]: CAMPUS

| Electrical properties             | dry / cond | Unit  | Test Standard |
|-----------------------------------|------------|-------|---------------|
| <b>ISO Data</b>                   |            |       |               |
| <sup>[C]</sup> Volume resistivity | 1E10 / -   | Ohm*m | IEC 62631-3-1 |

|                                |         |       |             |
|--------------------------------|---------|-------|-------------|
| [C] Electric strength          | 20 / -  | kV/mm | IEC 60243-1 |
| [C] Comparative tracking index | 500 / - | -     | IEC 60112   |
| <b>ASTM Data</b>               |         |       |             |
| Arc Resistance                 | 150 / - | s     | ASTM D 495  |

[C]: CAMPUS

| Other properties        | dry / cond | Unit              | Test Standard  |
|-------------------------|------------|-------------------|----------------|
| [C] Water absorption    | 0.6 / *    | %                 | Sim. to ISO 62 |
| [C] Humidity absorption | 1.5 / *    | %                 | Sim. to ISO 62 |
| [C] Density             | 1500 / -   | kg/m <sup>3</sup> | ISO 1183       |

[C]: CAMPUS

| Processing Recommendation Injection Molding | Value     | Unit | Test Standard |
|---|-----------|------|---------------|
| Pre-drying - Temperature                    | 80        | °C   | -             |
| Pre-drying - Time                           | 4         | h    | -             |
| Melt temperature                            | 285 - 305 | °C   | -             |
| Mold temperature                            | 65 - 95   | °C   | -             |
| Zone 1                                      | 280 - 310 | °C   | -             |
| Zone 2                                      | 280 - 310 | °C   | -             |
| Zone 3                                      | 280 - 310 | °C   | -             |
| Nozzle temperature                          | 280 - 310 | °C   | -             |

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Natural Color

### Additives

Lubricants, Release agent

### Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

### Features

Creep Resistance

### Chemical Resistance

General Chemical Resistance, Solvent Resistance, Grease Resistance, Hydrolytically Stable, Oil Resistance

### Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

### Applications

Automotive, General Purpose

### Regional Availability

North America, Europe, Asia Pacific